

# POWER FAIRING COAT

Cementitious Fairing Coat for Precast and In-Situ Concrete (Mortar)



## PRODUCT DESCRIPTION

Power Fairing Coat is a fine filled, fast-setting, cementitious mortar, specifically formulated for the repair of damaged concrete where only a thin layer is required. The specially selected cements and polymers contained in Power Fairing Coat produces a fast-setting mortar with exceptional adhesion to concrete and masonry materials with negligible shrinkage.

## ADVANTAGES & BENEFITS

- Good adhesion
- Fast setting
- Easy application
- Durable

## TYPICAL PROPERTIES

- Set Times @ 20°C  
Initial: 25 minutes Final: 50 minutes
- Compressive strength @ 20°C 28 days 20 MPa

## APPLICATION INSTRUCTION

Preparation: All contacted surfaces must be free of oil, grease or other contamination which may inhibit bond. Any cracked or weakened concrete should be removed prior to being repaired to provide a solid foundation. Scabbling or water blasting should be used to remove laitance and provide a mechanical key.

### Priming:

Priming with Power Grip B is essential to ensure good adhesion to the substrate. Where the substrate is very porous pre-dampening with water may be required. Free water on the surface will reduce the bond and ultimate strength.

### Mixing:

Power Fairing Coat is suitable for mixing using a drill and suitable paddle or by hand where only a small quantity is required. Use 5.0 - 5.5 liters of water per bag of Power Fairing Coat to achieve a smooth, soft mortar consistency. Excess water will reduce the final strength and make application of the render more difficult. Always add the powder to the water while mixing slowly to avoid lumps. Only mix that quantity of material that can be used within the setting time. Do not attempt to rework or retemper any partially set product.

## APPLICATION

Apply the mixed Power Fairing Coat to the substrate using a trowel to give the required finished thickness. The maximum thickness applied in any application should be limited to 5mm. Feather edging may be used in patch repairs.

## CURING

The application of a thin coat of Power Grip Bas a curing membrane will reduce premature drying in repairs subject to direct sun or strong winds.

## CLEAN UP

Clean all equipment with water immediately after use.

## PACKAGING

Power Fairing Coat is supplied in 20 kg bags. Power Grip B is supplied in 5- and 30-liter containers.

## ESTIMATING DATA

A 20 kg bag of Power Fairing Coat will cover approximately 4 m<sup>2</sup> at an average thickness of 3mm. Power Grip B is used at 5 to 7 m<sup>2</sup> per liter. A scabbled surface will reduce the area covered by the primer and topping.

## STORAGE

Power Fairing Coat is a cement-based product which must stored in a dry area off the ground.

## PRECAUTIONS

Do not use Power Fairing Coat in areas subject to rising damp or in wet areas. Where temperatures less than 10°C or greater than 35°C are encountered, contact our Technical Staff for specific advice. Power Fairing Coat is non toxic, but it is alkaline in nature. Any contact with eyes or skin should be washed off with clean water. Protective gloves and clothing should be worn.

Note: Material safety data sheets for these and all Power products are available on request. Read the MSDS and product label carefully before using. All reasonable care is taken in the compilation of this data sheet. All recommendations regarding use are made without guarantee as the conditions of use are beyond the control of the manufacturer/



[www.powerchemicalspk.com](http://www.powerchemicalspk.com) | Email Id: [info@powerchemicalspk.com](mailto:info@powerchemicalspk.com)

Office # 10-B, Ziarat Trade Center Tarnol Islamabad-Pakistan